

## Prepregs:



Prepregs made of Glass fabric style 7628 with epoxy resin for MLB and as per customer requirement.

## General Specification

### Prepreg For MLB

Prepreg Property

Fabric Type	Resin content %	Resin Flow %	Gel Time at 171° C sec	Typical Thickness mm
1080	65 ± 3	42 ± 3	130 ± 20	0.081
	62 ± 3	38 ± 3	130 ± 20	0.074
	53 ± 3	30 ± 3	130 ± 20	0.125
2116	50 ± 3	25 ± 3	130 ± 20	0.110
	47 ± 3	28 ± 3	130 ± 20	0.205
7628	44 ± 3	23 ± 3	130 ± 20	0.194

Note: Specification of prepreg are general range only, specific tolerance is available upon request

General information of shelf life ( storage):

Storage for one month at 20° C and 50% R.H.

Storage for one to three month at 5° C and 50% R.H.

Stabilize the prepreg at 25° C and 50% R.H.for 24 hours before use.